

洛氏、維氏、肖氏硬度換算表：

HRC(洛氏)	HV(洛克氏)	HRA	HS(肖氏)
81		92.5	
79		91.5	
77		90.5	
75		89.5	
73		88.5	
71		87.5	
69		86	
68	940	85.6	97
67	900	85	95
66	865	84.5	92
65	832	83.9	91
64	800	83.4	88
63	772	82.8	87
62	746	82.3	85
61	720	81.8	83
60	697	81.2	81
59	674	80.7	80
58	653	80.1	78
57	633	79.6	76
56	613	79	75
55	595	78.5	74
54	577	78	72
53	560	77.4	71
52	544	76.8	69
51	528	76.3	68
50	513	75.9	67
49	498	75.2	66
48	484	74.7	64
47	471	74.1	63
46	458	73.6	62
45	446	73.1	60
44	434	72.5	58
43	423	72	57
42	412	71.5	56

洛氏、維氏、肖氏硬度換算表（二）

HRC(洛氏)	HV(洛克氏)	HRA	HS(肖氏)
41	402	70.9	55
40	392	70.4	54
39	382	69.9	52
38	372	69.4	51
37	363	68.9	50
36	354	68.4	49
35	345	67.9	48
34	336	67.4	47
33	327	66.8	46
32	318	66.3	44
31	310	65.8	43
30	302	65.3	42
29	294	64.7	41
28	286	64.3	41
27	279	63.8	40
26	272	63.3	38
25	266	62.8	38
24	260	62.4	37
23	254	62	36
22	248	61.5	35
21	243	61	35
20	238	60.5	34
-18	230	-	33
-16	222	-	32
-14	213	-	31
-12	204	-	29
-10	196	-	28
-8	188	-	27
-6	180	-	26
-4	173	-	25
-2	166	-	24
0	160	-	24